AMENDMENTS TO THE SPECIFICATION

Please amend Chart 3A appearing on page 88 as follows:

| Epoxy Resin Mixture Ratio (%) | | | 2 | 2 | 2 | 2 | 2 | 2 | 2 | 2 | 2 | 0.5 | 12 |
|---|--------------------------------------|----|--------------------------|------|------|------|------|-------|------|------|------|------|------|
| SmFeN Coarse Magnet Powder 10%Sm-7%Fe-13%N (at%) | Mixture Ratio | | 1 | ı | 20 | 20 | 20 | 20 | 20 | 53 | 10 | 20 | 15 |
| | Average Grain Diameter (µm) | | 1 | 1 | 3 | 3 | 3 | 3 | 3 | 3 | 3 | 3 | 3 |
| | Surfactant | | | ı | Yes | No | No | Yes | Yes | Yes | Yes | Yes | Yes |
| | Mixture Ratio | | 86 | 86 | 78 | 78 | 78 | 78 | 78 | 45 | 88 | 79.5 | 73 |
| NdFeB Coarse Magnet Powder (Co-less) | Average Grain Diameter (µm) | | 106 | 106 | 106 | 106 | 106 | 45 35 | 425 | 106 | 106 | 106 | 106 |
| | Surfactant | | Yes | Yes | No | Yes | No | Yes | Yes | Yes | Yes | Yes | Yes |
| | Composition (at%) | Pr | 1 | ŧ | 0.1 | 0.1 | 0.1 | | • | | • | | |
| | | La | | • | , | , | | | | • | , | 1 | , |
| | | ప | | | | | | | | | | , | |
| | | Zr | | | | | | , | | | | | |
| | | NP | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 | 0.2 |
| | | Ga | 0.3 | 0.3 | 0.3 | 0.3 | 0.3 | 0.3 | 0.3 | 0.3 | 0.3 | 0.3 | 0.3 |
| | | Fe | Bal. | Bal. | Bal. | Bal. | Bal. | Bal. | Bal. | Bal. | Bal. | Bal. | Bal. |
| | | В | 6.4 | 6.4 | 6.2 | 6.2 | 6.2 | 6.4 | 6.4 | 6.4 | 6.4 | 6.4 | 6.4 |
| | | Dy | , | | | , | | 0.5 | 0.5 | | , | | , |
| | | PΝ | 12.5 | 12.5 | 12.7 | 12.7 | 12.7 | 13.5 | 13.5 | 12.5 | 12.5 | 12.5 | 12.5 |
| Sample No. | | | BI | B2 | CI | C2 | C3 | DI | D2 | BI | E2 | FI | F2 |
| | | | First Comparison Example | | | | | | | | | | |